

## **MACHINE SCREWS**





METRIC - ISO 14583 Pan Six-Lobe Machine Screws ISO 14583									
	Thread Pitch	D Head Diameter		H Height of Head		R Recess Diameter Recess	(	G	
Nominal Size							Recess Penetration		Recess Size
		Max	Min	Max	Min	Ref	Max	Min	
• M1.6	0.35	3.2	2.9	1.4	1.26	1.49	0.6		T5
M2	0.4	4.0	3.7	1.60	1.46	1.75	0.77	0.63	T6
M2.5	0.45	5.0	4.7	2.10	1.96	2.4	1.04	0.91	T8
МЗ	0.5	5.6	5.3	2.4	2.26	2.8	1.27	1.10	T10
M4	0.7	8.00	7.64	3.10	2.92	3.95	1.66	1.27	T20
M5	0.8	9.50	9.14	3.70	3.52	4.5	1.91	1.52	T25
M6	1	12.0	11.57	4.6	4.3	5.6	2.42	2.02	T30
Tolerance on Length		3mm: ±0.20			4-6mm: ±0.24			7-10mm: ±0.29	
		11-16mm: ±0.35			20-30mm: ±0.42			35-50mm: ±0.50	

<sup>•</sup> Dimensions for M1.6 are independent of the ISO 14583 standard.

Description	A pan head, straight shank fastener made of medium carbon steel with a metric thread pitch designed to go through a hole or nut that is pre-tapped to form a mating thread for the screw.	A pan head, straight shank fastener made of stainless steel with a metric thread pitch designed to go through a hole or nut that is pre-tapped to form a mating thread for the screw.		
Applications/ Advantages	Ideal for applications where extra driving torque is required, especially where fasteners are subject to repetitive vibration. Has a general purpose bearing area that can be substituted in most instances for round, truss or binding heads.	Design has a general purpose bearing area that can be substituted in most instances for round, truss or binding heads.  A2 is used in corrosive environments. A4 will provide a degree of protection from corrosion that is superior to A2.		
	Steel	Stainless		
Material	Medium carbon steel that conforms to the following chemical composition: <b>Carbon:</b> 0.25 - 0.55%; <b>Phosphorous:</b> 0.04% maximum; <b>Sulfur:</b> 0.05% maximum	A2 Stainless Steel and A4 Stainless Steel		
Heat Treatment	Class 8.8 machine screws shall be heat treated by quenching in a liquid medium from above the transformation temperature and reheating to a tempering temperature of 425°C.	-		
Hardness	Rockwell C 22 - 32	-		
Tensile Strength	640 N/mm² minimum			
Plating	See Appendix-A	Stainless screws are typically provided without additional finish.		